



# PRODUCT DATA SHEET

## ASTERIA Vinyl Sealer

### DESCRIPTION

ASTERIA CV Sealer is a post-catalyzed, alkyd amino sealer formulated to cure fast with excellent sanding properties and a long pot life. ASTERIA Vinyl Sealer exhibits superior adhesion and water resistance, and is a true, water clear conversion varnish sealer that does not contain any nitrocellulose. For wood substrates only. For interior use only.

PRODUCT NUMBERS / SHEENS	COATING PROPERTIES	PREPARATION INSTRUCTIONS
CVS-0500	<p><b>Viscosity:</b> 14-18 #2 Zahn  <b>Weight Solids:</b> 27.2%  <b>Volume Solids:</b> 20%  <b>Weight/Gallon:</b> 7.5 lbs./gal  <b>Coverage:</b> 319 sq. ft. per gallon at one mil dry film thickness.  <b>VOC (reg./coating):</b> 5.26 lbs./gl. or 631.1g/l  <b>VOC (act/material):</b> 4.54 lbs./gl. or 545 g/l  <b>VOC Ratio:</b> 2.2 lbs. VOC/lbs. Solid  <b>HAPS Ratio:</b> 0.36 lbs. HAPS/lbs. Solid</p> <p><b>Dry Times:</b>  <b>Air Dry:</b> at 78° F, relative humidity 50%            To touch: 8-10 minutes            To handle: 15 minutes            To sand/recoat: 25-30 minutes  <b>Force Dry:</b>            Flash: 8-10 minutes            Bake: 15 min @ 110° F            Cool down: 15 min            Stack immediately after cool down</p> <p>Relative humidity will affect the speed of drying. Ideal conditions are 75°F or warmer at 50% humidity or less. Dry time will be faster at higher temperatures and lower humidity and equally slower at colder temperatures and higher humidity.  <b>Dry Film Thickness:</b> For best results, the DFT for this sealer should be between 1-1.75 mils. Please refer to the PDS for the specific topcoat you are using for maximum DFT for the complete system.</p> <p><b>Pot Life:</b> 7 Days @ 77° F in a sealed container.</p> <p><b>Shelf Life Un-Catalyzed:</b> 18 months @77° F if unopened, and stored in a cool dry area. Always rotate stock.</p> <p><b>Storage:</b> Keep away from heat or sparks.</p>	<p><b>Catalyzation:</b>            Using CAT10-0700: Mix 100 parts CVS-0500 to 6 parts CAT10-0700 Catalyst (6% by volume)</p> <p>For gallon containers-Add one pre-measured 7 oz. bottle of CAT10-0700 per short-filled gallon            For 5 gallon pails. Add 35 oz of CAT10-0700 per short-filled pail.  <i>Gallon Fill level is 117 oz.,            Five Gallon Fill level is 585 oz.</i></p> <p><b>NOTE: DO NOT add more than the recommended amount of catalyst! This will not make the product cure faster or harder and may cause cracking, haziness, gloss issues, and will affect the integrity of the final product.</b></p> <p><b>Reduction:</b>  <b>Important:</b> Always catalyze <i>BEFORE</i> reducing!  <b>Thinning:</b> This product is supplied ready to spray (after catalyzation). If needed due to conditions in your facility, use SOL-9059 HAPs Free Reducer or SOL-9011 HAPs Free Thinner at levels not to exceed 5% by volume.*</p> <p><b>Retarder:</b> If a slower dry time is desired, use SOL-9012 Haps Free Retarder at levels not to exceed 4% by volume.*</p> <p>*Thinning this material may result in increasing the VOC levels of this product. Refer to your local regulations before thinning.</p> <p><b>Approved Companion Products</b>            ASTERIA AFCVRS-02XX Series            GemVar UCV-00XX Series</p>
PRODUCT ADVANTAGES		
<ul style="list-style-type: none"> <li>➤ Fast Cure</li> <li>➤ Water Clear</li> <li>➤ 7 Day Pot Life</li> <li>➤ Superb Sanding Properties</li> <li>➤ Containers Are Short Filled To Allow For The Addition Of Catalyst</li> <li>➤ Excellent UV Resistance</li> <li>➤ Meets Or Exceeds KCMA And ASTM Requirements When Applied To Manufacturer Specifications</li> <li>➤ Non-Photo Chemically Reactive</li> <li>➤ Phthalate Free</li> </ul> <p><i>Note: These numbers represent actual control values on a smooth, sanded substrate. Spray techniques, texture, and sealing as well as film thickness may give different results on actual work, but they may be used for comparison. To the best of our knowledge, the above technical data is true and accurate at the date of issuance but is subject to change without prior notice.</i></p>		

April, 2024

The following supersedes any provision contained in the forms, letters and papers of your company. This product is designed and intended for professional application only. All products should be thoroughly tested under application conditions prior to use. The information contained herein is believed to be reliable. **HOWEVER, GEMINI MAKES NO WARRANTY CONCERNING THIS PRODUCT, WHETHER EXPRESS OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** UNDER NO CIRCUMSTANCES SHALL GEMINI BE LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL, OR ANY OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH OF WARRANTY, STRICT LIABILITY, OR ANY OTHER LEGAL THEORY, ARISING OUT OF THE USE OR HANDLING OF THIS PRODUCT. THE SOLE REMEDY OF THE BUYER AND THE SOLE LIABILITY OF GEMINI FOR ANY CLAIMS SHALL BE LIMITED TO THE BUYER'S PURCHASE PRICE OF THE PRODUCT WHICH IS THE SUBJECT OF THE CLAIM OR THE AMOUNT ACTUALLY PAID FOR SUCH PRODUCT, WHICHEVER IS LESS. TECHNICAL ADVICE FURNISHED BY GEMINI SHALL NOT CONSTITUTE AN EXPRESS WARRANTY, WHICH IS EXPRESSLY DISCLAIMED. ALL TECHNICAL ADVICE GIVEN IS ACCEPTED AT THE RISK OF THE BUYER. **CAUTION: DANGER! FLAMMABLE! VAPORS MAY CAUSE FLASH FIRE. VAPOR HARMFUL. HARMFUL OR FATAL IF SWALLOWED. INJURIOUS TO EYES. KEEP OUT OF THE REACH OF CHILDREN!** BEFORE using this product it is essential that the "Material Safety Data Sheet" describing the product as well as the "Product Label" be reviewed. If your company does not have such information or has any questions, contact the manufacturer.



PRODUCT DATA SHEET CVS-0500 CONTINUED



**Substrate preparation:**

**New wood:** Remove any dirt, grease, glue or other contaminants. Moisture content of wood should be 7-9%.

Sand to 150-180 grit. Proper sanding of wood is absolutely critical to achieve the best color development and adhesion of the coating to the substrate.

**Old wood:** Strip old finishes completely and remove all contaminants from the surface. Make sure the surface is dry, sand as required. Finish same as new wood.



**Mixing Instructions: PRODUCT MUST BE CATALYZED.**

Mix material thoroughly before and during use. Material may be mixed by hand or mechanical agitation at moderate speed.

**To Catalyze:** Material should be agitated slowly while mixing in the catalyst. Mix or agitate thoroughly after adding catalyst and before use (5-10 minutes). This product has been short-filled to allow room for catalyst. Catalyze as follows:

Short filled Gallon: Add 7 oz CAT10-0700 (use supplied pre-measured bottle) to the short-filled gallon.

Short filled Five Gallon Pails: Add 35 oz of CAT10-0700 to the short-filled pail.

OR:

Mix 100 parts CVS-0500 to 6 parts CAT10-0700 (6% by volume).

Mixing Chart (examples for mixing various amounts):

CVS-0500	CAT10-0700
100 oz	6 oz
50 oz	3 oz
25 oz	1.5 oz
17 oz	1 oz



**Application:**

If staining, apply the approved Gemini stain of your choosing and let dry per the instructions on the PDS for that particular stain. Using conventional, HVLP, airless, or air assisted equipment, apply this product at 3-4 wet mils per coat. Let dry a minimum 25-30 minutes. Sand with 280-320 grit, no-fill sandpaper and remove sanding dust with clean compressed air, or tack rag. This product must be sanded in between coats to ensure proper adhesion.

Typically we recommend a coating system comprised of one coat of CVS-0500 applied at 3-4 mils wet film build and 1-2 coats of topcoat applied at 3-4 mils wet film build. Please refer to the Approved Companion Products section of this document for approved products.

Refer to the Product Data Sheet for the conversion varnish topcoat you are using for maximum dry film thickness recommendations.



**Recommended Tip Sizes:**

- Conventional Air            1.4-1.8 mm
- HVLP                            1.5-1.9 mm
- Airless                         10-13 thousandths
- Air Assisted Airless        11-13 thousandths



**Precautions:**

These products are intended for Professional use only. Do not proceed if you are planning on mixing with other finishing systems or other manufacturer's products. Gemini will not be held liable for finish failures due to the improper use of our products or deviation from our finishing recommendations.

**Equipment:**

All equipment used with this product must have plastic, stainless steel, or Teflon fluid passages and wetted parts.

**Containers:**

We supply this material in a lined container. All containers used in conjunction with storage and/or application of this product must be stainless steel, plastic, or otherwise acid resistant.

**Clean up:**

Use SOL-9011 Non HAPs Thinner or SOL-9059 HAPs Free Reducer to clean up all equipment. Dispose of in accordance with Federal, State, and Local regulation regarding pollution.

**Care and cleaning of this finish:** Use a mild dishwashing liquid and a damp cloth to remove food, grease, and other residue. Wipe dry. Do not use cleaners that contain ammonia, bleach, or abrasives as this may damage the finish.