



---

Product: S/G UV RC

Date: 03/09/2011

Code: UV-1117R

DOT: N/A

---

*SPECIFICATIONS:*

Wt/gal: 10.0±0.1 lbs/gal

%Solids:

Weight: 100±1

Volume: 100±1

Theoretical V.O.C.

Lbs/gal: 0.0

Grams/Liter:

Viscosity: 3000 cps (#3 spn @20 rpm Brookfield)

*CURED FILM PROPERTIES:*

Application: roller coat

Cure schedule: 3 Hg (medium pressure bulbs, 200 watts/in)

Substrate: wood

Gloss (60°/20°):55-60

Pencil Hardness ASTM D3363: pass 3H

% Crosshatch Adhesion ASTM D3359: 100

Impact (in. pounds) ASTM D 2794

Direct: N/A

Reverse: N/A

Humidity (hours) ASTM D4585: N/A

Salt Spray(hours) ASTM D117: N/A

Chemical Resistance ASTM D1308: 100 MEK rubs

Gloss Retention ASTM D523: N/A

Protect from freezing

*COMMENTS:*

Shelf Life – 1 year unopened containers stored at R.T. 50% R.H.

This Technical Data Sheet is accurate to the best of our knowledge. However, as applications, conditions and intended end use are beyond our control, no warranty as to fitness or merchantability is expressed or implied. Customers are urged to confirm their own results.